

Metričke dimenzije i težine po metru prema ASTM A 269 ili ASTM A 512

 OD mm	Wall thickness, mm						
	0.5	1.0	1.5	2.0	2.5	3.0	4.0
	 Weight, kg/m (conventional weights)						
6	0.069	0.126	0.17				
8		0.176	0.245				
10		0.226	0.321	0.403			
12		0.277	0.396	0.503			
14			0.462	0.604			
15		0.352	0.51	0.654			
16			0.547	0.705			
18			0.623				
20			0.698	0.888		1.28	
22			0.774	1.02			
25			0.887	1.16	1.43	1.66	
28			1.00	1.31			
30				1.41		2.04	
36				1.66			
38						2.64	3.42
40				1.91			
42				2.01			
50				2.42			

Napomena:

Za austenitne nerđajuće čelike množiti navedenu težinu sa 1.014.

Za feritne i martenzitne čelike množiti navedenu težinu sa 0.985.